## Amendments to the Claims

This listing of claims will replace all prior versions, and listings, of claims in the application:

## **Listing of Claims**:

- (Currently amended) A process of producing a fluorided catalyst metallocene catalyst component comprising contacting a nitrogenous metallocene compound with a fluoriding agent comprising a Bronsted acid fluorided acid for a time sufficient to form a fluorided metallocene catalyst compound; wherein the nitrogenous metallocene compound comprises at least one nitrogenous leaving group "X", wherein X is described by the formula  $-N(R^{\alpha})_2$ , wherein each  $R^{\alpha}$  is independently selected from  $C_1$  to  $C_{10}$  alkyls,  $C_6$  to  $C_{20}$  aryls,  $C_7$  to  $C_{21}$  alkylaryls,  $C_7$  to  $C_{21}$  arylalkyls, and halide, carboxylate silyl or hydroxy-substituted versions thereof.
- (Previously presented) The process of claim 1, wherein the nitrogenous metallocene catalyst compound is described by the formulae

wherein M is a Group 4, 5 or 6 atom;

Cp<sup>A</sup> and Cp<sup>B</sup> are each bound to M and are the same or different and are selected from the group consisting of cyclopentadienyl, indenyl, tetrahydroindenyl, fluorenyl, and substituted derivatives of each;

(A) is a divalent bridging group bound to each of Cp<sup>A</sup> and Cp<sup>B</sup>;

n is 0, 1 or 2; and

X is as defined.

3. (Cancelled)

- 4. (Original) The process of claim 1, wherein the fluoriding agent is a fluorided anhydrous acid.
- 5. (Original) The process of claim 1, wherein from 1 to 10 equivalents of fluoriding agent are contacted with the nitrogenous metallocene compound.
- 6. (Original) The process of claim 1, wherein the fluoriding agent is selected from the group consisting of HF, HBF<sub>4</sub>, HPF<sub>6</sub>, HBF<sub>4</sub>OMe<sub>2</sub> and combinations thereof.
- 7. (Original) The process of claim 2, wherein n is 2.
- 8. (Original) The process of claim 2, wherein the Cp<sup>A</sup> and Cp<sup>B</sup> are selected from the group consisting of substituted cyclopentadienyl and substituted tetrahydroindenyl; the substituent groups selected from the group consisting of C<sub>1</sub> to C<sub>10</sub> alkyls and C<sub>6</sub> to C<sub>20</sub> aryls.
- 9. (Original) The process of claim 7, wherein the substituent groups are selected from C<sub>1</sub> to C<sub>6</sub> alkyls.
- 10. (Original) The process of claim 2, wherein M is zirconium or hafnium.
- 11. (Original) The process of claim 1, wherein contacting the nitrogenous metallocene compound with the fluoriding agent subsequently forms an organic compound and a neutral nitrogenous compound and additionally comprising separating the neutral nitrogenous compound from the organic compound to form the fluorided metallocene catalyst compound.
- 12. (Original) The process of claim 2, wherein (A) is selected from divalent C<sub>1</sub> to C<sub>5</sub> hydrocarbons and silicon-containing hydrocarbons.

- 13. (Original) The process of claim 1, wherein contacting the nitrogenous metallocene compound with the fluoriding agent results in a fluorided metallocene compound yield of 50% or more.
- 14. (Original) The process of claim 1, wherein contacting the nitrogenous metallocene compound with the fluoriding agent results in a fluorided metallocene compound yield of 80% or more.
- 15. (Original) The process of claim 1, wherein contacting the nitrogenous metallocene compound with the fluoriding agent results in a fluorided metallocene compound yield of 90% or more.
- 16. (Original) The process of claim 2, wherein M is zirconium.
- 17. (Original) The process of claim 1, further comprising drying the fluorided metallocene compound in the presence of magnesium sulfate.
- 18. (Original) The process of claim 1, wherein contacting the nitrogenous metallocene compound with the fluoriding agent comprises contacting the nitrogenous metallocene compound with 2 or more equivalents of the fluoriding agent.
- 19. (Original) The process of claim 1, wherein contacting the nitrogenous metallocene compound with the fluoriding agent comprises contacting the nitrogenous metallocene compound with 2 or less equivalents of the fluoriding agent.
- 20. (Currently amended) A process of producing a polyolefin comprising combining a metallocene catalyst system comprising a fluorided metallocene catalyst component and monomers selected from the group consisting of ethylene and C<sub>3</sub> to C<sub>12</sub> olefins, wherein the fluorided metallocene catalyst component is produced

by contacting a nitrogenous metallocene compound with a <u>Bronsted acid</u> fluoriding agent for a time sufficient to form a fluorided metallocene catalyst compound, followed by isolation of the fluorided metallocene catalyst compound and formation of a metallocene catalyst system; wherein the nitrogenous metallocene compound comprises at least one nitrogenous leaving group "X", wherein X is described by the formula –N(R<sup>α</sup>)<sub>2</sub>, wherein each R<sup>α</sup> is independently selected from C<sub>1</sub> to C<sub>10</sub> alkyls, C<sub>6</sub> to C<sub>20</sub> aryls, C<sub>7</sub> to C<sub>21</sub> alkylaryls, C<sub>7</sub> to C<sub>21</sub> arylalkyls, and halide, carboxylate silyl or hydroxy-substituted versions thereof.

21. (Previously presented) The process of claim 20, wherein the nitrogenous metallocene catalyst compound is described by the formulae

wherein M is a Group 4, 5 or 6 atom;

Cp<sup>A</sup> and Cp<sup>B</sup> are each bound to M and are the same or different and are selected from the group consisting of cyclopentadienyl, indenyl, tetrahydroindenyl, fluorenyl, and substituted derivatives of each;

(A) is a divalent bridging group bound to each of Cp<sup>A</sup> and Cp<sup>B</sup>; n is 0, 1 or 2; and X is as defined.

- 22. (Cancelled)
- 23. (Original) The process of claim 20, wherein the fluoriding agent is a Bronsted acid comprising fluorine.
- 24. (Original) The process of claim 20, wherein the fluoriding agent is a fluorided anhydrous acid.

7137800044

- (Original) The process of claim 20, wherein the olefins are selected from the 25. group consisting of ethylene and C3 to C12 a-olefins.
- (Original) The process of claim 20, wherein the olefins and catalyst system are 26. combined in a fluidized bed gas phase reactor at a polymerization temperature of from 50°C to 120°C.
- The process of Claim 20, wherein the catalyst system further 27. (Original) comprises a support material.
- The process of Claim 27, wherein the support material is silica 28. (Original) calcined at a temperature of from 800°C to 900°C.
- The process of Claim 28, wherein the catalyst system further 29. (Original) comprises an alumoxane activator.
- (Original) The process of Claim 20, wherein the metallocene catalyst system 30. further comprises a Ziegler-Natta catalyst component or a Group 15-containing catalyst component.
- (Original) The process of Claim 20, wherein a polyolefin is produced having a 31. density in the range of from 0.880 to 0.925 g/cm<sup>3</sup>.
- (Previously Presented) The process of Claim 30, wherein a bimodal polyolefin is 32. produced having a density in the range of from 0.930 to 0.970 g/cm<sup>3</sup>.

## 33-34 (Cancelled)

(Currently amended) A process of producing a fluorided catalyst metallocene 35. catalyst component comprising contacting a nitrogenous metallocene compound with a fluoriding agent comprising a Bronsted acid fluorided acid for a time

sufficient to form a fluorided metallocene catalyst compound; wherein contacting the nitrogenous metallocene compound with the fluoriding agent comprises contacting the nitrogenous metallocene compound with 2 or more equivalents of the fluoriding agent.

36. (Previously Presented) The process of claim 35, wherein the nitrogenous metallocene catalyst compound is described by the formulae

wherein M is a Group 4, 5 or 6 atom;

Cp<sup>A</sup> and Cp<sup>B</sup> are each bound to M and are the same or different and are selected from the group consisting of cyclopentadienyl, indenyl, tetrahydroindenyl, fluorenyl, and substituted derivatives of each;

(A) is a divalent bridging group bound to each of Cp<sup>A</sup> and Cp<sup>B</sup>;

n is 0, 1 or 2, and

X is selected from the group consisting of amides, amines, imines, nitriles and combinations thereof.

- 37. (Previously Presented) The process of claim 36, wherein X is described by the formula -N(R<sup>α</sup>)<sub>2</sub>, wherein each R<sup>α</sup> is independently selected from C<sub>1</sub> to C<sub>10</sub> alkyls, C<sub>6</sub> to C<sub>20</sub> aryls, C<sub>7</sub> to C<sub>21</sub> alkylaryls, C<sub>7</sub> to C<sub>21</sub> arylalkyls, and halide, carboxylate silyl or hydroxy-substituted versions thereof; wherein any two R<sup>α</sup> groups may form a ring system of from 4 to 10 carbons that may also comprise an atom selected from Groups 13-16.
- 38. (Previously Presented) The process of claim 35, wherein the fluoriding agent is a fluorided anhydrous acid.
- 39. (Previously Presented) The process of claim 35, wherein from 1 to 10 equivalents of fluoriding agent are contacted with the nitrogenous metallocene compound.

- 40. (Previously Presented) The process of claim 35, wherein the fluoriding agent is selected from the group consisting of HF, HBF<sub>4</sub>, HPF<sub>6</sub>, HBF<sub>4</sub>OMe<sub>2</sub> and combinations thereof.
- 41. (Previously Presented) The process of claim 36, wherein n is 2.
- 42. (Previously Presented) The process of claim 36, wherein the Cp<sup>A</sup> and Cp<sup>B</sup> are selected from the group consisting of substituted cyclopentadienyl and substituted tetrahydroindenyl, the substituent groups selected from the group consisting of C<sub>1</sub> to C<sub>10</sub> alkyls and C<sub>6</sub> to C<sub>20</sub> aryls.
- 43. (Previously Presented) The process of claim 35, wherein contacting the nitrogenous metallocene compound with the fluoriding agent subsequently forms an organic compound and a neutral nitrogenous compound and additionally comprising separating the neutral nitrogenous compound from the organic compound to form the fluorided metallocene catalyst compound.
- 44. (Previously Presented) The process of claim 35, wherein contacting the nitrogenous metallocene compound with the fluoriding agent results in a fluorided metallocene compound yield of 50% or more.
- 45. (Previously Presented) The process of claim 35, wherein contacting the nitrogenous metallocene compound with the fluoriding agent results in a fluorided metallocene compound yield of 80% or more.
- 46. (Previously Presented) The process of claim 35, wherein contacting the nitrogenous metallocene compound with the fluoriding agent results in a fluorided metallocene compound yield of 90% or more.